
Avery Dennison[®] MPI 2122 Matte Grey Removable

Satin White Blockout Calendered Vinyl Removable (Formerly MPI 2012)

Features

- Excellent printability and handling on all eco-solvent & solvent inkjet printers •
- Satin finish for superior low glare appearance •
- Dimensionally StaFlat liner provides easy converting properties .
- Excellent dimensional stability during use
- . Good conformability to flat and simple curved surfaces
- Very good outdoor durability and performance .
- Opaque film and grey adhesive provide exceptional blockout performance
- Easy and clean removability with heat for up to 1 year •

Description



Formatted: Bullets and Numbering

Formatted: Bullets and Numbering

$\overline{}$	Adhesive: Grey Removable
\sim	acrylic
	Bomovability: Up to 1 year

Removability: Up to 1 year

(unprinted)



X

Backing: Two side PE coated Staflat[™] paper

Outdoor life: Up to 6 years

Application surface: Flat, simple curves

Conversion

- Flat bed cutters
- Friction fed cutters
- Die cutting
- Thermal transfer
- Screen printing
- Cold overlaminating Water based inkjet
- Eco solvent inkjet
- Solvent inkjet
- UV Cured inkjet*

Common Applications

- Flat sided trucks
- Cars and vans
- Trains and light rail
- . POP & Display
- Outdoor advertising •

Uses

Avery Dennison MPI 2122 Matte Grey Removable is a satin white intermediate vinyl film designed for use in a wide range of outdoor advertising and general signage applications where excellent outdoor durability, removability and excellent print quality are required.

Digital Media Product Data Sheet

Avery Dennison[®] MPI 2122 Matte Grey Removable

Physical characteristics

General

Caliper, facefilm	ISO 534	86 micron
Caliper, facefilm & adhesive	ISO 534	106 micron
Dimensional stability	DIN 30646	0.4 mm
Opacity	ISO 2471	***
Adhesion, initial	FINAT FTM-1, stainless steel	***
Adhesion, ultimate	FINAT FTM-1, stainless steel	***
Removability ^	Smooth OEM painted surfaces	Up to 3 years
Flammability		Self extinguishing
Shelf life	Stored at 20-25°C / 45-55 % RH	1 year
Durability **	Vertical exposure	Up to 6 years unprinted

^ Not removable when applied to nitrocellulose paints, fresh screenprint inks, ABS, polystyrene & certain types of PVC

Thermal

Application temperature	Minimum: + 4°C
Temperature range	- 40°C to + 82°C

Chemical

Resistant to most mild acids, alkalies and salts

Note:

Materials have to be properly dried and cured before further processing, like laminating, varnishing, trimming, contour cutting or application. The residual solvents can otherwise change the products' specific features and properties.

Test Methods

Dimensional stability: Is measured on a 150 \times 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70 °C, after which the shrinkage is measured.

Adhesion: (FTM-1, FINAT) is measured by peeling a specimen at a 180 ° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

Flammability: A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

Temperature range: A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. I hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

Warrantv

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in and are wanted to be there not be defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

**Durability

Durability is based on exposure conditions in the Asia Pacific region. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing north in the southern hemisphere or south in the northern hemisphere: in areas of long high temperature exposure such as northern Australia; in industrially polluted areas or high altitudes, exterior performance will be decreased.

*Compatible with most media and ink combinations. Test prior to use

***Information unavailable at time of printing.

Chemical Resistance: All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. I hour after removing the panel from the fluid, the structure is the immersed for any identification. specimen is examined for any deterioration

Corrosion Resistance: A specimen applied to aluminium is exposed to saline mist (5% salt) at 35%. After exposure, the film is removed and the panel is examined for traces of corrosion.

Avery Dennison Graphics Solutions Asia Pacific

www.graphicsap.averydennison.com